



LOSE WOLLE

Data sheet



Item number
Consumption
Raw material
Application

5 kg: LO500500BR24 10 kg: LW100100BR24
Density of 18 kg/m³ is sufficient
100% wool sustainable, durable, recyclable, without synthetic additives
Window- and hollow space insulation, Wooden construction

PRODUCT DESCRIPTION



- **Carded wool fleece** for filling joints and cracks between beams, walls and hollow spaces on windows and doors.
- Darning wool is also suitable for **roof windows** in the roofing frame.

WOOL PROTECTION



- **IONIC PROTECT®** biocide-free wool protection, long-term tested by EAD/CUAP standards and patented procedure
- Is a slight alteration of the molecular protein structure of the wool fibre through a **plasma-ion treatment**. This specific process is unique as it permanently prevents the wool from being a nutritional source for wool parasites
- Through the wool protection, our products have an **unlimited shelf-life**.



INSTALLATION

- Fill up the hollow spaces with a scrapper or spread the wool fleece manually.

PROPERTIES



Sheep wool insulation



Air purification



Humidity regulation



Sound insulation
Fire protection



Sustainable



Wool protection

LOSE WOLLE

Data sheet



SOLENA NEWSLETTER

Receive relevant news every three weeks

<https://bit.ly/3iKhtKg>

Subscribe now!



 lehnerwool

 isolena.at

 lehnerwool

FORM OF DELIVERY

DIMENSIONS

5 or 10kg per packaging unit (PU)

Article	Thickness (mm)	Width (mm)	Lengths (mm)	Item /PU	kg PU
LW05	-	-	-	1	5,00
LW10	-	-	-	1	10,00

TECHNICAL DATA

European technical approval	ETA-07/0214
Nature Plus®	0103-1006-099-1
Thermal conductivity λ_{tr}	0,038 W/mK
Fire behaviour according to EN 13501-1 from 18kg/m ³	D-s2, d0; CH: RF3
Vapour diffusion resistance factor μ	1
Specific heat capacity c	1760 J/kgK
Mould growth intensity according to EN ISO 846	0

ECOLOGICAL PARAMETERS

Compliant with the NaturePlus® Life cycle assessment ISOLENA

Use of non-renewable primary energy without the non-renewable primary energy carriers used as raw material (PENRE [MJ, lower calorific value])	23,44	MJ / kg
Global warming potential Total of GHG emissions and CO ₂ storage (GWP 100 total)	0,83	kg CO ₂ -äquiv. / kg
Acidification potential of soil and water (AP)	4,63E-03	kg SO ₂ -äquiv. / kg
Potential for the formation of tropospheric ozone (POCP)	8,04E-04	kg C ₂ H ₄ -äquiv. / kg
Eutrophication potential (EP)	2,08E-03	kg PO ₄ ³⁻ -äquiv. / kg



Energy Globe Award